



Insulating Fire Brick

BNZ Materials, Inc

Effective: Mar-16		BNZ 28
Classification Group	ISO 2245 ASTM C 155	150-0.9-L 28
Classification Temperature	°C	1540
Density	ASTM C 134 g/cm ³	0.88
Cold Crushing Strength	Flat ASTM C 133 MPa Edge	2.3
Cold Modulus of Rupture	ASTM C 133 MPa	1.5
Permanent Linear Change	ASTM C 210 %	-0.7
24h soak at Temperature, °C		1510
Linear Thermal Expansion	%	0.65
Reversible, Max.		
Deformation under Hot Load	ASTM C 16 %	-0.1
69 kPa load, 1½h at Temperature, °C		1204
Thermal Conductivity	ASTM C 182 W/(mK)	
Mean Temperature, °C		
200		0.33
400		0.34
600		0.35
800		0.37
1000		0.38
1200		0.40
Chemical Analysis	%	
Al ₂ O ₃		67.0
SiO ₂		30.5
Fe ₂ O ₃		0.3
TiO ₂		0.9
CaO + MgO		0.3
Na ₂ O + K ₂ O		1.0
Dimensional Tolerances	Standard Square	
Dimensions mm		± 0.8
Out of Squareness %		≤ 0.5

The above physical and chemical properties of Insulating Fire Brick represent values obtained on standard squares in accordance with accepted test methods and are subject to normal manufacturing variations. This information is supplied as a technical service and may change without notice. Results should not be used for specification purposes, unless agreed with seller.

BNZ Materials, Inc.
 191 Front Street,
 Zelienople, PA 16063, USA

Tel: +1-724-452-8650
www.bnzmaterias.com
info@bnzmaterias.com

Distributor: