



**MOSCONI** s.r.l.



# SUPER INSULATING BRICK

## ISOLMOS 550

Effective: November 2015

			ISOLMOS 550
<b>Classification</b>	ISO 2245 : 2006		<b>85-L</b>
<b>Density</b>	ISO 5016 : 1995	Kg/m <sup>3</sup>	<b>500</b>
<b>Max. service temperature</b>		°C	<b>900</b>
<b>Cold crushing strength</b>	ISO 8895 : 2006	MPa	<b>2.5</b>
<b>Linear Reheat Change</b> 12h soak @ Temperature (°C)	ISO 2477 : 2005	%	<b>&gt; -1.0</b> <b>850</b>
<b>Thermal Conductivity</b> Mean Temperature 200°C 400°C 600°C 800°C	ASTM C 182-88 : 2009	W/m <sup>2</sup> K	<b>0.13</b> <b>0.15</b> <b>0.17</b>
<b>Chemical Analysis</b> SiO <sub>2</sub> Al <sub>2</sub> O <sub>3</sub> TiO <sub>2</sub> Fe <sub>2</sub> O <sub>3</sub> CaO MgO K <sub>2</sub> O Na <sub>2</sub> O P <sub>2</sub> O <sub>5</sub>	XRF	%	<b>65.0</b> <b>15.0</b> <b>0.5</b> <b>4.0</b> <b>7.0</b> <b>1.3</b> <b>5.0</b> <b>1.1</b> <b>0.5</b>
<b>Thermal Expansion (max.)</b>	EN 821-1 : 1995	%	<b>0.4</b>
<b>Refractoriness</b>	ISO 528 : 1983	°C	<b>1140</b>
<b>Refractoriness Under Load, T<sub>05</sub></b> Load: 0.05 MPa	ISO 1893 : 2008	°C	<b>810</b>
<b>Total Porosity</b>	ISO 5017 : 2013	%	<b>80</b>
<b>Dimensional Tolerances</b> <b>Machined standard squares</b> <b>Trimmed standard squares</b> Length Width Thickness		mm	<b>± 1.0</b> <b>± 2.0</b> <b>± 2.0</b> <b>± 1.5</b>

**MOSCONI S.r.l.**

Villa Fornace 4

26021 Annicco (CR), Italy

Tel: +39-0374-79020

[www.mosconi.com](http://www.mosconi.com)

[info@mosconi.com](mailto:info@mosconi.com)



The above physical and chemical properties of Insulating Brick represent values obtained on standard squares in accordance with accepted test methods and are subject to normal manufacturing variations. This information is supplied as a technical service and may change without notice. Results should not be used for specification purposes, unless agreed with seller.

*Distributed by:*

**UNIC PRODUCTS S.r.l.**

Via Cerca 26, 20090 Caleppio di Settala (MI), Italy Tel: +39-02 9589 8184

[www.unicproducts.com](http://www.unicproducts.com)

[info@unicproducts.com](mailto:info@unicproducts.com)