



Insulating Fire Brick

Effective: Mar-16		T 24
Classification Group	ISO 2245 ASTM C 155	135-0.6-L
Classification Temperature	°C	1320
Density	ASTM C 134 g/cm ³	0.65
Cold Crushing Strength	Flat ASTM C 133 MPa Edge	2.0
Cold Modulus of Rupture	ASTM C 133 MPa	1.3
Permanent Linear Change	ASTM C 210 % 24h soak at Temperature, °C	-0.5 1290
Linear Thermal Expansion	% Reversible, Max.	0.60
Deformation under Hot Load	ASTM C 16 % 69 kPa load, 1½h at Temperature, °C	-0.1 1093
Thermal Conductivity	ASTM C 182 W/(mK) Mean Temperature, °C	
	200	0.16
	400	0.18
	600	0.21
	800	0.24
	1000	0.28
	1200	
Chemical Analysis	%	
Al ₂ O ₃		34.0
SiO ₂		63.0
Fe ₂ O ₃		1.3
TiO ₂		0.5
CaO + MgO		0.5
Na ₂ O + K ₂ O		0.9
Dimensional Tolerances	Standard Square	
Dimensions	mm	± 1.0
Out of Squareness	%	≤ 0.5

The above physical and chemical properties of Insulating Fire Brick represent values obtained on standard squares in accordance with accepted test methods and are subject to normal manufacturing variations. This information is supplied as a technical service and may change without notice. Results should not be used for specification purposes, unless agreed with seller.

Tianjin New Century Refractories Co., Ltd.
A-1207 ICTC, 59 Machang Road,
Tianjin, China 300203

Tel: +86-22-8558-9019
<http://www.tncrltd.com>
sales@tncrltd.com

Sales Office in Europe:



UNIC PRODUCTS S.r.l.
Via Cerca 26,
20090 Calepio di Settala (MI), Italy

Tel: +39-2 9589 8184
<http://www.unicproducts.com>
info@unicproducts.com